

	Al%	Si	Fe	Cu	Mn	Mg	Zn	Ti	Cr
Mesure 1	96.756	1.089	0.520	0.379	0.412	0.130	0.602	0.024	0.019
Mesure 2	96.763	1.088	0.509	0.377	0.405	0.131	0.612	0.024	0.020
Minimum	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000	0.000
Moyenne	96.759	1.089	0.515	0.378	0.409	0.131	0.607	0.024	0.019
RSD%	0.01	0.06	1.43	0.35	1.20	0.77	1.18	0.57	0.96
Maximum	100.000	100.000	100.000	100.000	100.000	100.000	100.000	100.000	100.000

	Ni	Pb	Sn	Na	Ca	P	Sb	Sr	Bi
Mesure 1	0.014	0.024	0.012	0	0	8	0	2	0
Mesure 2	0.014	0.023	0.012	0	0	8	0	2	0
Minimum	0.000	0.000	0.000	0	0	0	0	0	0
Moyenne	0.014	0.023	0.012	0	0	8	0	2	0
RSD%	0.00	1.04	0.44	-	-	0.19	-	4.13	141.42
Maximum	100.000	100.000	100.000	1000000	1000000	1000000	1000000	1000000	1000000

	Cd	Li	Hg	V	B	Zr	Be	Co	As
Mesure 1	2	0	0	83	1	27	0	5	0
Mesure 2	2	0	0	85	1	27	0	5	4
Minimum	0	0	0	0	0	0	0	0	0
Moyenne	2	0	0	84	1	27	0	5	2
RSD%	10.44	3.70	-	1.41	25.08	0.65	0.50	0.20	153.15
Maximum	1000000	1000000	1000000	1000000	1000000	1000000	1000000	1000000	1000000

	Ga	Ag
Mesure 1	117	4
Mesure 2	119	4
Minimum	0	0
Moyenne	118	4
RSD%	1	1
Maximum	1000000	1000000